

Total LLDPE LL 1810 H Linear Low Density Polyethylene - Blown Film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

Material Notes:

LL 1810 H is an ethylene-butene copolymer produced in a gas phase reactor. It is designed for delivering competitive performance in most blown film applications. LL 1810 H can be processed at high output rates with moderate extrusion pressure, good bubble stability and gauge control on blown film machine designed for LLDPE. LL 1810 H can advantageously be blended with LDPE or other PE resins used in blown film mono extrusion or coextrusion to improve film properties. LL 1810 H is suited for many applications in the field of consumer, industrial, food or hygiene packaging such as collation shrink, liners, Form-Fill-Seal, heavy-duty sacks, refuse sacks or other bags and non-packaging applications like agriculture films e.g. tunnel and mulching films. Contains antioxidant, slip agent and antiblock agent. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-LLDPE-LL-1810-H-Linear-Low-Density-Polyethylene-Blown-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.921 g/cc	0.921 g/cc	ISO 1183
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
Antiblock Level	3200 ppm	3200 ppm	
Slip Level	1500 ppm	1500 ppm	Erucamide

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.0 MPa	1600 psi	ISO 527-3
Film Tensile Strength at Yield, TD	11.0 MPa	1600 psi	ISO 527-3
Film Elongation at Break, MD	800 %	800 %	ISO 527-3
Film Elongation at Break, TD	850 %	850 %	ISO 527-3
Elmendorf Tear Strength, MD	7.10 g/micron	180 g/mil	ISO 6383-2
Elmendorf Tear Strength, TD	12.2 g/micron	310 g/mil	ISO 6383-2
Dart Drop Test	150 g	0.331 lb	ISO 7765-1
Film Tensile Strength at Break, MD	38.0 MPa	5510 psi	ISO 527-3
Film Tensile Strength at Break, TD	33.0 MPa	4790 psi	ISO 527-3
1% Secant Modulus, MD	215 MPa	31200 psi	ISO 178
1% Secant Modulus, TD	245 MPa	35500 psi	ISO 178

Mechanical Properties	Metric	English	Comments
Melting Point	122 °C	252 °F	ISO 11357
Vicat Softening Point	100 °C	212 °F	ISO 306

Optical Properties	Metric	English	Comments
Haze	12 %	12 %	ISO 14782
Gloss	57 %	57 %	at 45°; ASTM D2457

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 220 °C	356 - 428 °F	Extrusion Temp
Die Opening	>= 0.180 cm	>= 0.0709 in	
Blow-up Ratio (BUR)	2.0 - 3.0	2.0 - 3.0	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China