

## Total Lacqtene® 2001 TN 46 HDPE pipe (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

### Material Notes:

LACQTENE® 2001 TN 46 is a high density polyethylene produced by the gas phase polymerization process with hexene as comonomer.

LACQTENE® 2001 TN 46 is used for sewage pipe, smooth protective conduit, telecom conduit, and sheet extrusion. LACQTENE® 2001 TN 46 is best processed between 190 and 230°C. Information provided provided by Total Petrochemicals. Total Petrochemicals includes former Fina and Atofina plastics product lines.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Total-Lacqtene-2001-TN-46-HDPE-pipe-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Total-Lacqtene-2001-TN-46-HDPE-pipe-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.945 g/cc	0.0341 lb/in <sup>3</sup>	ISO 1183
Oxidative Induction Time (OIT)	>= 20 min	>= 20 min	200°C; EN 728
Melt Flow	0.10 g/10 min	0.10 g/10 min	ISO 1133
	@Load 2.16 kg	@Load 4.76 lb	
	0.45 g/10 min	0.45 g/10 min	ISO 1133
	@Load 5.00 kg	@Load 11.0 lb	
High Load Melt Index	11 g/10 min	11 g/10 min	ISO 1133
	@Load 21.6 kg	@Load 47.6 lb	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	59	59	ISO 868
Tensile Strength, Yield	24.0 MPa	3480 psi	ISO 527-2
Elongation at Break	>= 700 %	>= 700 %	ISO 527-2
Flexural Modulus	1.00 GPa	145 ksi	ISO 178-2
Izod Impact, Notched (ISO)	20.0 kJ/m <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	ISO 180
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	129 °C	264 °F	
Vicat Softening Point	120 °C	248 °F	ISO 306

Descriptive Properties	Value	Comments
------------------------	-------	----------

Food Status  
Descriptive Properties

This material conforms to both European and American Food contact regulations.  
Value

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China