

Total PPC 11712 Polypropylene, Heterophasic Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

ATOFINA Propylene 11712 is a nucleated controlled-rheology heterophasic copolymer. PPC 11712 is characterized by good stiffness and impact resistance as well as low shrinkage and low warpage. It has been formulated for excellent antistatic properties.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPC-11712-Polypropylene-Heterophasic-Copolymer.php

Physical Properties	Metric	English	Comments
Bulk Density	0.525 g/cc	0.0190 lb/in ³	ISO 1183
Density	0.905 g/cc	0.0327 lb/in ³	ISO 1183
Melt Flow	70 g/10 min @Load 2.16 kg, Temperature 230 °C	70 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	84	84	ISO 2039-2
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527-2
Elongation at Yield	5.0 %	5.0 %	ISO 527-2
Tensile Modulus	1.25 GPa	181 ksi	ISO 527-2
Flexural Modulus	1.15 GPa	167 ksi	ISO 527-2
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	ISO 180
	4.00 kJ/m ² @Temperature -20.0 °C	1.90 ft-lb/in ² @Temperature -4.00 °F	ISO 179
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179
	0.400 J/cm ² @Temperature -20.0 °C	1.90 ft-lb/in ² @Temperature -4.00 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	120°C per hour; ISO 75-2
Deflection Temperature at 1.8 MPa (264 psi)	55.0 °C	131 °F	120°C per hour; ISO 75-2

Thermal Properties	Metric	English	Comments
	140 °C	284 °F	10N-50°C per hour; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China