

Total PS CPDS 818E Flame Retardant Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

Material Notes:

POLYSTYRENE (PS) COMPOUND (CPDS) 818E is a high impact brominated flame retardant polystyrene. A combination of high flow and high heat stability gives excellent processability and reduced cycle times. PS CPDS 818E can be supplied in both natural and colored forms. Main Characteristics: DBDPE free, Excellent UV stability, High flow, high heat stability, UL94 V0 @ 1.6 mm. Applications: Cover for electrical equipment, TV covers, office automation. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PS-CPDS-818E-Flame-Retardant-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	<= 1.13 g/cc	<= 1.13 g/cc	ISO 1183
Water Absorption	<= 0.10 %	<= 0.10 %	ISO 62
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	
Melt Flow	10 g/10 min @Load 5.00 kg, Temperature 200 °C	10 g/10 min @Load 11.0 lb, Temperature 392 °F	ISO 1133H

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.0 MPa	3630 psi	ISO 527-2
Elongation at Break	40 %	40 %	ISO 527-2
Flexural Modulus	2.30 GPa	334 ksi	ISO 178
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	180/1A

Thermal Properties	Metric	English	Comments
Vicat Softening Point	85.0 °C @Load 5.10 kg	185 °F @Load 11.2 lb	50°C per hour; ISO 306B50
Flammability, UL94	V-0 @Thickness 2.00 mm	V-0 @Thickness 0.0787 in	All colors
	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	Black

Processing Properties	Metric	English	Comments
Melt Temperature	<= 260 °C	<= 500 °F	

Processing Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China