

## Toyobo PELPRENE™ P150B-05 Polyester TPE, Non-smell, Non-deposit

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester TPE , Polyester, TP , Polyester Thermoplastic Elastomer

### Material Notes:

Features: Polyester TPE, Non-smell, Non-deposit  
Information provided by Toyobo.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Toyobo-PELPRENE-P150B-05-Polyester-TPE-Non-smell-Non-deposit.php](http://www.lookpolymers.com/polymer_Toyobo-PELPRENE-P150B-05-Polyester-TPE-Non-smell-Non-deposit.php)

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in <sup>3</sup>	ASTM D792
Moisture Absorption at Equilibrium	0.36 %	0.36 %	23°C, 65% RH
Linear Mold Shrinkage	0.013 cm/cm @Thickness 2.00 mm	0.013 in/in @Thickness 0.0787 in	
Melt Index of Compound	20 g/10 min @Temperature 230 °C	20 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	98	98	JIS K6301
Hardness, Shore D	57	57	ASTM D2240
Tensile Strength at Break	38.0 MPa	5510 psi	ASTM D638
Elongation at Break	500 %	500 %	ASTM D638
50% Modulus	0.0196 GPa	2.84 ksi	ASTM D638
Flexural Modulus	0.289 GPa	41.9 ksi	ASTM D790
Compressive Modulus	0.0191 GPa	2.77 ksi	0.1; ASTM D695
Resilience	59	59	JIS K6301
Izod Impact, Notched	NB	NB	ASTM D256
Tear Strength	176 kN/m	1000 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	10	10	ASTM D1044
Compression Set	60 %	60 %	JIS K6301

Thermal Properties	Metric	English	Comments
CTE, linear	140 µm/m-°C	77.8 µin/in-°F	TMA

Thermal Properties	@Temperature 20.0 °C Metric	@Temperature 68.0 °F English	Comments
Melting Point	212 °C	414 °F	By DSC
Maximum Service Temperature, Air	117 °C	243 °F	Heat deflection temperature, load unknown; ASTM D648
Vicat Softening Point	190 °C	374 °F	ASTM D1525
Brittleness Temperature	<= -65.0 °C	<= -85.0 °F	JIS K6301
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+14 ohm-cm	2.00e+14 ohm-cm	ASTM D257
Dielectric Strength	30.0 kV/mm	762 kV/in	JIS K2111

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China