

Toyobo PELPRENE™ S2002FB Polyester TPE, Flame Resistant

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester TPE , Polyester, TP , Polyester Thermoplastic Elastomer

Material Notes:

Features: Polyester TPE, Flame Resistant Information provided by Toyobo.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Toyobo-PELPRENE-S2002FB-Polyester-TPE-Flame-Resistant.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ASTM D792
Moisture Absorption at Equilibrium	0.38 %	0.38 %	23°C, 65% RH
Linear Mold Shrinkage	0.013 cm/cm @Thickness 2.00 mm	0.013 in/in @Thickness 0.0787 in	
Melt Index of Compound	12 g/10 min @Temperature 230 °C	12 g/10 min @Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	98	98	JIS K6301
Hardness, Shore D	57	57	ASTM D2240
Tensile Strength at Break	26.9 MPa	3900 psi	ASTM D638
Elongation at Break	560 %	560 %	ASTM D638
50% Modulus	0.0166 GPa	2.41 ksi	ASTM D638
Flexural Modulus	0.230 GPa	33.4 ksi	ASTM D790
Compressive Modulus	0.0158 GPa	2.29 ksi	0.1; ASTM D695
Resilience	60	60	JIS K6301
Izod Impact, Notched	NB	NB	ASTM D256
Tear Strength	160 kN/m	913 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	12	12	ASTM D1044
Compression Set	65 %	65 %	JIS K6301

Thermal Properties	Metric	English	Comments
CTE, linear	130 µm/m-°C	72.2 µin/in-°F	TMA

Thermal Properties	@Temperature 20.0 °C Metric	@Temperature 68.0 °F English	Comments
Melting Point	210 °C	410 °F	By DSC
Maximum Service Temperature, Air	110 °C	230 °F	Heat deflection temperature, load unknown; ASTM D648
Vicat Softening Point	185 °C	365 °F	ASTM D1525
Brittleness Temperature	<= -65.0 °C	<= -85.0 °F	JIS K6301
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+13 ohm-cm	4.00e+13 ohm-cm	ASTM D257
Dielectric Strength	25.0 kV/mm	635 kV/in	JIS K2111

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China