

Toyobo Vylopet® EMC415 PET/PBT Blend

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , PET + PBT Unreinforced , Polyethylene Terephthalate (PET)

Material Notes:

Key Feature: HB UL-94 Class
Applications: accessory components
PET/PBT blends suggested for glossy surfaces. General features of Vylopet® include heat resistance, good mechanical properties, high dielectric strength and tracking resistance, chemical & weather resistance, and processability. Information provided by Toyobo Co., Ltd

Order this product through the following link:

http://www.lookpolymers.com/polymer_Toyobo-Vylopet-EMC415-PETPBT-Blend.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ASTM D792
Water Absorption	0.050 %	0.050 %	ASTM D570
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	
Linear Mold Shrinkage, Transverse	0.012 cm/cm	0.012 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	95	95	ASTM D785
Tensile Strength, Ultimate	84.0 MPa	12200 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Yield Strength	123 MPa	17800 psi	ASTM D790
Flexural Modulus	5.20 GPa	754 ksi	ASTM D790
Compressive Yield Strength	93.0 MPa	13500 psi	ASTM D695
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ASTM D256
Taber Abrasion, mg/1000 Cycles	28	28	ASTM D1044

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	DSC
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	25.0 kV/mm @Thickness 2.00 mm	635 kV/in @Thickness 0.0787 in	ASTM D149
Arc Resistance	126 sec	126 sec	ASTM D495
Comparative Tracking Index	250 V	250 V	IEC test

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China