

Tra-Con Tra-Bond 854-1

Category : Polymer , Thermoset

Material Notes:

Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-854-1.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	87	87	
Adhesive Bond Strength	20.7 MPa	3000 psi	Lap shear, alum to alum

Processing Properties	Metric	English	Comments
Cure Time	180 min	3.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	

Descriptive Properties	Value	Comments
Color	Blue	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China