

Tra-Con Tra-Bond F175T One-Part Thixotropic UV Curing Adhesive

Category : Polymer , Adhesive , Thermoset

Material Notes:

TRA-BOND F175T is a thixotropic, one part UV curing adhesive designed for bonding metals, ceramics and most rigid polymers. It is an excellent adhesive for fiber optic terminations where fast cure with ultraviolet light is desired. It is also recommended for electronic applications as it has very low ionic impurities. TRA-BOND F175T is a unique system which produces very little shrinkage upon cure. It is an excellent choice for high humidity environments or applications requiring thermal cycling. HANDLING: TRA-BOND F175T should be stored with an air space to ensure maximum stability. Do not purge with nitrogen. Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-F175T-One-Part-Thixotropic-UV-Curing-Adhesive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	Mixed

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	

Thermal Properties	Metric	English	Comments
CTE, linear	130 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	72.2 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Maximum Service Temperature, Air	110 $^{\circ}\text{C}$	230 $^{\circ}\text{F}$	
Minimum Service Temperature, Air	-55.0 $^{\circ}\text{C}$	-67.0 $^{\circ}\text{F}$	
Glass Transition Temp, Tg	11.0 $^{\circ}\text{C}$	51.8 $^{\circ}\text{F}$	Ultimate Tg

Processing Properties	Metric	English	Comments
Cure Time	0.0167 min	0.000278 hour	400 W/inch @ 1"
	0.0667 min	0.00111 hour	400 W/inch @ 6"
	0.750 min	0.0125 hour	9 mW/inch @ 1"

Descriptive Properties	Value	Comments
Color	Light Yellow	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China