

Tra-Con Tra-Duct 921U01

Category : Polymer , Thermoset

Material Notes:

Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Duct-921U01.php

Physical Properties	Metric	English	Comments
Viscosity	1.72e+6 cP	1.72e+6 cP	Mixed (ssa #14/6r)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	85.0 @Treatment Temp. 121 °C, Time 2400 sec	85.0 @Treatment Temp. 250 °F, Time 0.667 hour	
Adhesive Bond Strength	35.5 MPa	5150 psi	Lap shear, alum to alum, 40 min @ 121°C

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	112 °C	234 °F	Ultimate Tg

Processing Properties	Metric	English	Comments
Cure Time	40.0 min @Temperature 121 °C	0.667 hour @Temperature 250 °F	

Descriptive Properties	Value	Comments
Color	Gray	Mixed/Cured

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China