

Tra-Con Tra-Duct 926H01

Category : Polymer , Thermoset

Material Notes:

Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Duct-926H01.php

Physical Properties	Metric	English	Comments
Viscosity	4800 cP	4800 cP	Mixed (cp #52, 10 rpm)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	42	42	1 hr @ 70°C
Hardness, Shore D	93	93	1 hr @ 70°C
Adhesive Bond Strength	6.21 MPa	900 psi	Lap shear, alum to alum, 1 hr @ 70°C

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	20.0 °C	68.0 °F	Ultimate Tg

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.0050 ohm-cm	0.0050 ohm-cm	cured 1 hr @ 70°C

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 70.0 °C	@Temperature 158 °F	
	120 min	2.00 hour	
	@Temperature 60.0 °C	@Temperature 140 °F	

Descriptive Properties	Value	Comments
Color	Light Yellow	Hardener
	Silver	Resin/Mixed/Cured
Thixotropic Index	2	5 rpm/50 rpm

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China