

Trelleborg Emerson & Cuming Eccobond® 11 Heat Cure Catalyst

Category : Polymer , Adhesive , Thermoset

Material Notes:

Emerson & Cuming 11 Eccobond® Heat Cure Catalyst General purpose, low viscosity, elevated temperature curing. Long working life. Yields cured coatings with excellent chemical resistance. Subject to partial crystallization at temperatures below 65°C. (Crystals can be removed by gently warming to 65°C and maintaining until all crystals have been dissolved) Cure Type: Heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-11-Heat-Cure-Catalyst.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------------------------|------------------------------------|----------|
| Density | 1.10 g/cc | 0.0397 lb/in³ | |
| Viscosity | 35 - 60 cP @Temperature 25.0 °C | 35 - 60 cP @Temperature 77.0 °F | Mixed |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 155 °C | 311 °F | |
| Minimum Service Temperature, Air | -55.0 °C | -67.0 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|--------------------------------------|---|-----------|
| Cure Time | 120 - 240 min @Temperature 100 °C | 2.00 - 4.00 hour @Temperature 212 °F | |
| | 240 - 960 min @Temperature 150 °C | 4.00 - 16.0 hour @Temperature 302 °F | |
| Pot Life | >= 240 min @Temperature 25.0 °C | >= 240 min @Temperature 77.0 °F | 100 grams |

| Descriptive Properties | Value | Comments |
|------------------------|------------|----------|
| Color | Dark Brown | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China