

Trelleborg Emerson & Cuming Stycast® TU-906 Two-Component Polyurethane Flexible Encapsulant

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced , Polyurethane, TS

Material Notes:

Emerson & Cuming TU-906 Stycast® Two-Component Polyurethane Flexible Encapsulant Description Good thermal shock and moisture resistance. Good chemical resistance. Low viscosity. Mix Ratio (by weight) = 100:400 Cure Type: Room Temp or Heat Bonding Type: Polyurethane

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Stycast-TU-906-Two-Component-Polyurethane-Flexible-Encapsulant.php

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in ³	
Viscosity	3100 cP @Temperature 25.0 °C	3100 cP @Temperature 77.0 °F	Mixed

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 °C	266 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	>= 120 min	>= 2.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China