

## UBE 7034B Nylon 6/12 Copolymer Film

Category : Polymer , Film , Thermoplastic , Nylon , Nylon 612 , Nylon 612, Unreinforced

### Material Notes:

Specialties: High transparency Good thermoform-ability Low W.V.T.R High shrink-ability Lower extrusion temperature Processing: Best match for co-extrusion with EVOH resins. Typical Applications: Cereal packages Flavor barrier (compare with HDPE) Form-fill-seal (Air blown) Information provided by UBE.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_UBE-7034B-Nylon-612-Copolymer-Film.php](http://www.lookpolymers.com/polymer_UBE-7034B-Nylon-612-Copolymer-Film.php)

Physical Properties	Metric	English	Comments
Relative Viscosity	3.71 - 3.89 cP	3.71 - 3.89 cP	96% H2SO4
	4.0 - 4.2 cP	4.0 - 4.2 cP	98% H2SO4

Thermal Properties	Metric	English	Comments
Melting Point	195 - 205 °C	383 - 401 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	190 - 200 °C	374 - 392 °F	C1
	200 - 210 °C	392 - 410 °F	C2
	210 - 220 °C	410 - 428 °F	C3
	220 - 240 °C	428 - 464 °F	C4
	230 - 250 °C	446 - 482 °F	AD
	230 - 250 °C	446 - 482 °F	CF
	230 - 250 °C	446 - 482 °F	D1- D4

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China