

## UBE R300 Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE)

**Material Notes:**

Description: UBE Polyethylene is polymerized at high pressure using a tubular reactor. Production conditions are strictly controlled ensuring the product's superior physical and mechanical properties including transparency and glossiness, and making the material ideal for further processing. Transparency: Superior transparency and glossiness even for applications involving processing of thick objects. Ease of Processing: Excellent fluidity and melt tension characteristics suited to a wide range of molding methods. Inflation molding - can be molded into even thick or wide products with superior bubble stability. Extrusion lamination - can be drawn down even at high speed. Blow molding - can be molded producing a very smooth surface. Injection molding - can be molded even into very thin products. Strength: Good balance in length and breadth with superior tearing strength lengthways. Application: Thick objects Shrinkage Features: Toughness

Information provided by UBE.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_UBE-R300-Polyethylene.php](http://www.lookpolymers.com/polymer_UBE-R300-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	0.35 g/10 min	0.35 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	54	54	ASTM D2240
Tensile Strength at Break	21.0 MPa	3050 psi	ASTM D638
Elongation at Break	750 %	750 %	ASTM D638
Flexural Strength	15.0 MPa	2180 psi	Olsen; ASTM D747

Thermal Properties	Metric	English	Comments
Vicat Softening Point	93.0 °C	199 °F	ASTM D1525
Brittleness Temperature	<= -75.0 °C	<= -103 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China