

Unifrax Fiberfrax® Fibermax Bulk Mullite High-Temperature Fiber

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

In addition to Fiberfrax Bulk Fibers, Unifrax has the ability to produce many different specialty fibers that provide a variety of desirable performance properties for certain applications. These fibers can be classified into the following general categories: High-Index Fibers High-Temperature Fibers Large-Diameter Fibers Milled Fibers Unifrax manufactures two high-temperature specialty fibers for use in applications beyond recommended operating temperatures of 2300°F (1260°C). Bulk 8000 is made from high-purity alumina, zirconia, and silica raw materials. This chemistry, along with the unique manufacturing process, provides a fiber which can withstand continuous operating temperatures up to 2450°F (1345°C). Fibermax® Bulk Fiber is a high-temperature, polycrystalline mullite fiber. Fibermax fiber can withstand continuous operating temperatures up to 2800°F (1540°C) and is virtually shot free. Fibermax fibers can be blended with regular alumina-silicate Fiberfrax fibers to increase the thermal stability of the blended product beyond that of high-purity bulk fiber. Information Provided by Unifrax I LLC

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unifrax-Fiberfrax-Fibermax-Bulk-Mullite-High-Temperature-Fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	3.00 g/cc	3.00 g/cc	

Thermal Properties	Metric	English	Comments
Melting Point	1870 °C	3400 °F	
Maximum Service Temperature, Air	1540 °C	2800 °F	Recommended Operating Temperature

Component Elements Properties	Metric	English	Comments
Al2O3	72 - 75 %	72 - 75 %	
SiO2	25 - 28 %	25 - 28 %	

Descriptive Properties	Value	Comments
Color	White	
Fiber Index (%)	95+	
Temperature Grade (°C)	1650	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China