

Von Roll Isola IMI Varnish 74010A Epoxy Varnish for Electrical Insulation

Category : Polymer , Thermoset , Epoxy , Solventless Epoxy Varnish, Electrical Insulation

Material Notes:

Data provided by Von Roll Isola USA. Flash Point: 19°C. Average solids: 60%. Usage Notes: Use with IMI 74010 hardener for final coat over field coils, windings, and heavy duty motors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Von-Roll-Isola-IMI-Varnish-74010A-Epoxy-Varnish-for-Electrical-Insulation.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	
Viscosity	<= 50 cP	<= 50 cP	Hardener
	170 cP	170 cP	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	105 °C	221 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	39.0 kV/mm	991 kV/in	

Processing Properties	Metric	English	Comments
Processing Temperature	135 °C	275 °F	Suggested baking time at this temperature is 0.5-1 hr.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China