

Vyncolit X611 Novolac Phenolic

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Glass Filled

Material Notes:

Glass fiber filled phenolic molding compound with excellent mechanical and thermal properties. UL listed. USES: Complex precision parts with thin cross section and good mechanical properties e.g. insulators, spacers, edge connectors, coil former, timer parts and computer components. Information provided by Vyncolit, a Sumitomo Bakelite Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Vyncolit-X611-Novolac-Phenolic.php

Physical Properties	Metric	English	Comments
Bulk Density	0.650 g/cc	0.0235 lb/in ³	Powder Density; ISO 60
Density	1.65 g/cc	0.0596 lb/in ³	Relative Density; ISO 1183
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	Injection Molding; ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	90.0 MPa	13100 psi	ISO 527
Elongation at Break	0.70 %	0.70 %	Tensile; ISO 527
	1.5 %	1.5 %	Flexure; ISO 178
Tensile Modulus	15.0 GPa	2180 ksi	ISO 527
Flexural Strength	200 MPa	29000 psi	At Rupture; ISO 178
Flexural Modulus	14.5 GPa	2100 ksi	ISO 178
Compressive Strength	250 MPa	36300 psi	ISO 604
Charpy Impact Unnotched	0.950 J/cm ²	4.52 ft-lb/in ²	ISO 179
Charpy Impact, Notched	0.360 J/cm ²	1.71 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	23.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	12.8 $\mu\text{in}/\text{in}\cdot\text{°F}$	TMA
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	35.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	19.4 $\mu\text{in}/\text{in}\cdot\text{°F}$	TMA
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75 Af
	V-0	V-0	

Thermal Properties	Metric	English	Comments
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Shrinkage	0.15 %	0.15 %	Post Shrinkage; ISO 2577

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	DIN 53482
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 93
Insulation Resistance	7.50e+10 ohm	7.50e+10 ohm	Wet; 24 hours in water; IEC 167
	1.00e+11 ohm	1.00e+11 ohm	Dry; IEC 167
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 243
Comparative Tracking Index	125 V	125 V	IEC 112

Descriptive Properties	Value	Comments
Color	Black, Green	
ISO type	PF 2 C1	
Main Filler	Glass Fiber	
Molding Method	Compression, transfer, injection	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China