

## Wanhua Chemical Wanthane® WHT-1295B Polyester Based TPU

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

**Material Notes:**

Good mechanical properties, good extrusion stability, low cost  
Information provided by Wanhua Chemical Group Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wanhua-Chemical-Wanthane-WHT-1295B-Polyester-Based-TPU.php](http://www.lookpolymers.com/polymer_Wanhua-Chemical-Wanthane-WHT-1295B-Polyester-Based-TPU.php)

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	97	97	ASTM D2240
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength	32.0 MPa	4640 psi	ASTM D412
Elongation at Break	480 %	480 %	ASTM D412
100% Modulus	0.0180 GPa	2.61 ksi	ASTM D412
300% Modulus	0.0250 GPa	3.63 ksi	ASTM D412
Tear Strength	180 kN/m	1030 pli	ASTM D624
Abrasion	60	60	Abrasion resistance, mm <sup>&lt;sup&gt;3&lt;/sup&gt;</sup> ; ISO 4649

Processing Properties	Metric	English	Comments
Processing Temperature	195 - 210 °C	383 - 410 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China