

Wanhua Chemical Wanthane® WHT-1570 Polyester Based TPU

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Plasticizer free, excellent abrasion & slip resistance, low temperature flexibility, good mechanical properties, good processability
Information provided by Wanhua Chemical Group Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wanhua-Chemical-Wanthane-WHT-1570-Polyester-Based-TPU.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	ASTM D2240
Tensile Strength	30.0 MPa	4350 psi	ASTM D412
Elongation at Break	700 %	700 %	ASTM D412
100% Modulus	0.00350 GPa	0.508 ksi	ASTM D412
300% Modulus	0.00650 GPa	0.943 ksi	ASTM D412
Tear Strength	75.0 kN/m	428 pli	ASTM D624
Abrasion	50	50	Abrasion resistance, mm ³ ; ISO 4649

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 195 °C	356 - 383 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China