

## Washington Penn Homopolymer Polypropylene 20% Calcium Carbonate Filled

Category: Polymer, Thermoplastic, Polypropylene (PP), Polypropylene with 20% Calcium Carbonate (CaCO3) Filler

## **Material Notes:**

Calcium carbonate-filled polypropylene compounds have been tailored specifically to meet the requirements of each of the major automobile producers. Grades are available to meet FDA food and drug packaging requirements. These products have excellent mold detail and surface reproduction with fast set-up times. They are also available in an array of colors. Information provided by Washington Penn Plastic Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Washington-Penn-Homopolymer-Polypropylene-20-Calcium-Carbonate-Filled.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in³	ASTM D792
Filler Content	20 %	20 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.3 MPa	4100 psi	ASTM D638
Elongation at Break	240 %	240 %	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Flexural Modulus	1.90 GPa	275 ksi	1% Secant; ASTM D790
	2.07 GPa	300 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256
Gardner Impact	16.5 J	12.2 ft-lb	ASTM D5420
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	98.9 °C	210 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China