

## Wellman Wellamid® GF13-66 22LH-N 13% Glass Fiber Reinforced Nylon 66, Lubricated & Heat Stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 10% Glass Fiber Filled

### Material Notes:

Typical Applications: Radio and TV components, dishwasher roller carriages, chain saw oil reservoirs, gears, housings, door & window latches, power hand tool housings, high temperature devices. Data provided by the manufacturer, Wellman Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-GF13-66-22LH-N-13-Glass-Fiber-Reinforced-Nylon-66-Lubricated-Heat-Stabilized.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-GF13-66-22LH-N-13-Glass-Fiber-Reinforced-Nylon-66-Lubricated-Heat-Stabilized.php)

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.35 %	1.35 %	Approximate 24 hr.
Linear Mold Shrinkage	0.0050 - 0.0090 cm/cm	0.0050 - 0.0090 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	105 MPa	15200 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Flexural Yield Strength	175 MPa	25400 psi	ISO 178
Flexural Modulus	5.00 GPa	725 ksi	ISO 178
Izod Impact, Notched	0.400 J/cm	0.749 ft-lb/in	ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	ISO 75
Flammability, UL94	HB @Thickness 0.790 mm	HB @Thickness 0.0311 in	From Wellman QC Laboratory Testing; UL 94

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China