

## Wellman Wellamid® GF1750-BK1 50% Glass Fiber Reinforced Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled

**Material Notes:**

Description: Glass Fiber Reinforced Nylon 6 Information provided by Wellman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-GF1750-BK1-50-Glass-Fiber-Reinforced-Nylon-6.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-GF1750-BK1-50-Glass-Fiber-Reinforced-Nylon-6.php)

Physical Properties	Metric	English	Comments
Density	1.59 g/cc	0.0574 lb/in <sup>3</sup>	ISO 1183-87
Filler Content	50 %	50 %	
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	200 MPa	29000 psi	ISO 527-93
Elongation at Break	1.7 %	1.7 %	ISO 527-93
Flexural Strength	275 MPa	39900 psi	ISO 178-93
Flexural Modulus	14.6 GPa	2120 ksi	ISO 178-93
Izod Impact, Notched (ISO)	13.5 kJ/m <sup>2</sup>	6.42 ft-lb/in <sup>2</sup>	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ISO 75-93

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China