

Wellman Wellamid® GF33-66 22LH-N 33% Glass Fiber Reinforced Nylon 66, Lubricated & Heat Stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 30% Glass Fiber Filled

Material Notes:

Typical Applications: Radio and TV components, dishwasher roller carriages, chain saw oil reservoirs, gears, housings, door & window latches, power hand tool housings, high temperature devices. Data provided by the manufacturer, Wellman Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GF33-66-22LH-N-33-Glass-Fiber-Reinforced-Nylon-66-Lubricated-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in ³	ISO 1183
Water Absorption	1.25 %	1.25 %	Approximate 24 hr.
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	190 MPa	27600 psi	ISO 527
Elongation at Break	3.0 %	3.0 %	ISO 527
Flexural Yield Strength	280 MPa	40600 psi	ISO 178
Flexural Modulus	9.30 GPa	1350 ksi	ISO 178
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	ISO 75
Flammability, UL94	HB @Thickness 0.790 mm	HB @Thickness 0.0311 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China