

Wellman Wellamid® GFT13-66 XE-N 13% Impact Modified Glass Reinforced Nylon 66/6, Lubricated & Heat Stabilized

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/Nylon 6 Blend, Glass Fiber Filled

Material Notes:

Typical Applications: Machinery gear trains and linkage, conveyor belt links, fasteners, auto under hood and door parts, automotive door handles, appliance parts, sporting goods, lawn and garden equipment. Data provided by the manufacturer, Wellman Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GFT13-66-XE-N-13-Impact-Modified-Glass-Reinforced-Nylon-666-Lubricated-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Water Absorption	1.2 %	1.2 %	Approximate 24 hr.
Linear Mold Shrinkage	0.0080 - 0.012 cm/cm	0.0080 - 0.012 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	85.0 MPa	12300 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Flexural Yield Strength	120 MPa	17400 psi	ISO 178
Flexural Modulus	3.80 GPa	551 ksi	ISO 178
Izod Impact, Notched	0.900 J/cm	1.69 ft-lb/in	ISO 180

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75
Flammability, UL94	HB @Thickness 0.790 mm	HB @Thickness 0.0311 in	From Wellman QC Laboratory Testing; UL 94

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	282 - 310 °C	540 - 590 °F	
Middle Barrel Temperature	277 - 304 °C	530 - 580 °F	
Front Barrel Temperature	271 - 299 °C	520 - 570 °F	
Nozzle Temperature	271 - 304 °C	520 - 580 °F	
Melt Temperature	271 - 304 °C	520 - 580 °F	

Processing Properties	Metric	English	Comments
Mold Temperature	71.1 - 93.3 °C	160 - 200 °F	
Drying Temperature	79.4 °C	175 °F	Opened bags and gaylord boxes
Dry Time	2 - 4 hour	2 - 4 hour	Opened bags and gaylord boxes
Moisture Content	0.050 - 0.20 %	0.050 - 0.20 %	During molding to prevent hydrolytic degradation
	<= 0.20 %	<= 0.20 %	In shipping bags, ready to mold
Injection Pressure	34.5 - 138 MPa	5000 - 20000 psi	
Back Pressure	0.345 MPa	50.0 psi	
Screw Speed	30 - 120 rpm	30 - 120 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China