

## Wellman Wellamid® MRT1487 N Nylon 66, 32% Mineral Reinforced, Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Mineral Filled, Impact Grade

### Material Notes:

All information provided by Wellman Engineered Resins.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wellman-Wellamid-MRT1487-N-Nylon-66-32-Mineral-Reinforced-Impact-Modified.php](http://www.lookpolymers.com/polymer_Wellman-Wellamid-MRT1487-N-Nylon-66-32-Mineral-Reinforced-Impact-Modified.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ISO 1183-87
Linear Mold Shrinkage, Flow	0.016 - 0.020 cm/cm	0.016 - 0.020 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.014 - 0.018 cm/cm	0.014 - 0.018 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	ISO 527-93
Elongation at Break	15 %	15 %	ISO 527-93
Flexural Strength	100 MPa	14500 psi	ISO 178-93
Flexural Modulus	3.60 GPa	522 ksi	ISO 178-93
Izod Impact, Notched (ISO)	10.0 kJ/m <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75-93

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China