

Wieland Auropal W-2 Solder

Category : Metal , Nonferrous Metal , Precious Metal , Gold Alloy , Silver Alloy , Solder/Braze Alloy

Material Notes:

Solder supplied as strip (0.18 oz. roll)Information provided by WielandDental

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wieland-Auropal-W-2-Solder.php

Component Elements Properties	Metric	English	Comments
Copper, Cu	4.0 %	4.0 %	
Gold, Au	62 %	62 %	
Silver, Ag	22 %	22 %	
Zinc, Zn	12 %	12 %	

Processing Properties	Metric	English	Comments
Processing Temperature	750.0 °C	1382 °F	Flow Temp
Melt Temperature	720.0 - 750.0 °C	1328 - 1382 °F	

Descriptive Properties	Value	Comments
Color	yellow	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China