

Zeon Chemicals HyTemp® AR71 Polyacrylate Curative

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

HyTemp AR71 contains acrylic esters with a small percentage of a chlorine cure site monomer. Vulcanizates have excellent oil, heat, and compression set resistance. Contains acrylic esters with a small percentage of a chlorine cure site monomer. Vulcanizates have excellent oil, heat, and compression set resistance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zeon-Chemicals-HyTemp-AR71-Polyacrylate-Curative.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	42 - 54	42 - 54	Zeon Test #404
Ash	<= 0.60 %	<= 0.60 %	Zeon Test #873

Descriptive Properties	Value	Comments
Heat Loss (%) Max	0.7	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China