

## Zircar Zirconia Buster M-15 Alumina Boards, Discs & Cylinders Insulation

Category : Ceramic , Machinable Ceramic , Oxide , Aluminum Oxide

### Material Notes:

Zircar alumina insulation Type M Buster is a rigid, fibrous ceramic material produced by vacuum forming alumina fibers with silica binders in BusterM that form a thermal shock resistant mullite bond. Standard board densities are 15, 30, 35 and 45 pounds per cubic foot. Buster is available in boards, cylinders and custom machined parts. All Buster boards are pre-fired for organic-free use. Their fine grain quality and uniform binder distribution enables precision machining. All these features make Buster an ideal insulation material for hot face insulation, setters

Information provided by Zircar Zirconia

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Zircar-Zirconia-Buster-M-15-Alumina-Boards-Discs-Cylinders-Insulation.php](http://www.lookpolymers.com/polymer_Zircar-Zirconia-Buster-M-15-Alumina-Boards-Discs-Cylinders-Insulation.php)

Physical Properties	Metric	English	Comments
Density	0.240 g/cc	0.00868 lb/in <sup>3</sup>	
Porosity	93 %	93 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1.45 MPa	210 psi	
Compressive Yield Strength	0.207 MPa	30.0 psi	2% compression

Thermal Properties	Metric	English	Comments
CTE, linear	5.00 µm/m-°C	2.78 µin/in-°F	
Specific Heat Capacity	1.05 J/g-°C	0.250 BTU/lb-°F	
Melting Point	1870 °C	3400 °F	
Maximum Service Temperature, Air	1650 °C	3000 °F	
Shrinkage	4.00 % @Temperature 1700 °C, Time 3600 sec	4.00 % @Temperature 3090 °F, Time 1.00 hour	

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	85 %	85 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China