

3M 9039 Double Coated Tapes with Adhesive 300

Category : Polymer , Adhesive

Material Notes:

3M™ Double Coated Tapes with 3M™ Adhesive 300 feature a thin polyester film for dimensional stability and improved handling with ease of die cutting and laminating. The high tack adhesive provides relatively high initial adhesion and good shear holding power to a variety of surfaces. The carrier also provides easier handling during slitting and die cutting. Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-9039-Double-Coated-Tapes-with-Adhesive-300.php

Physical Properties	Metric	English	Comments
Thickness	12.7 microns	0.500 mil	Carrier
	38.1 microns	1.50 mil	Faceside Adhesive
	38.1 microns	1.50 mil	Backside Adhesive
	76.2 microns	3.00 mil	Liner Caliper
	88.9 microns	3.50 mil	Tape

Mechanical Properties	Metric	English	Comments
Peel Strength	0.73407 kN/m	4.1875 pli	to stainless steel, 90°, 15 min RT; ASTM D3330
	0.79981 kN/m	4.5625 pli	to ABS, 90°, 2 mil al foil, 72 hr RT; ASTM D3330
	0.84363 kN/m	4.8125 pli	to Polyester, 90°, 2 mil al foil, 72 hr RT; ASTM D3330
	0.877 kN/m	5.00 pli	to Polycarbonate, 90°, 2 mil al foil, 72 hr RT; ASTM D3330
	0.8984 kN/m	5.125 pli	to stainless steel, 90°, 72 hr RT; ASTM D3330
	1.074 kN/m	6.125 pli	to stainless steel, 90°, 72 hr at 70°C; ASTM D3330
	1.4134 kN/m	8.0625 pli	to stainless steel, 180°, 2 mil al foil, 72 hr RT; ASTM D3330

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.0 °C	180 °F	Long term
	121 °C	250 °F	Short term

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Shelf Life Processing Properties	24.0 Month Metric	24.0 Month English	Comments
-------------------------------------	----------------------	-----------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China