

3M 9472 Adhesive Transfer Tapes with Adhesive 300

Category : Polymer , Adhesive

Material Notes:

3M™ Adhesive Transfer Tapes with 3M™ Adhesive 300 offer excellent adhesion to a wide variety of surfaces, including low surface energy plastics and foam. This pressure sensitive acrylic adhesive family is available in several thicknesses for a wide variety of surface bonding and provides a variety of liner configurations to help ensure excellent process flexibility. Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-9472-Adhesive-Transfer-Tapes-with-Adhesive-300.php

Physical Properties	Metric	English	Comments
Thickness	88.9 microns	3.50 mil	Liner
	127 microns	5.00 mil	Adhesive

Mechanical Properties	Metric	English	Comments
Peel Strength	0.60259 kN/m	3.4375 pli	Polypropylene, 90° peel, 12"/min, 2 mil aluminum, 72 hr RT; ASTM D3330
	0.66833 kN/m	3.8125 pli	Polypropylene, 90° peel, 12"/min, 2 mil aluminum, 72 hr at 70°C; ASTM D3330
	0.8984 kN/m	5.125 pli	Polycarbonate, 90° peel, 12"/min, 2 mil aluminum, 72 hr RT; ASTM D3330
	1.074 kN/m	6.125 pli	Stainless Steel, 90° peel, 12"/min, 2 mil aluminum, 72 hr RT; ASTM D3330
	1.249 kN/m	7.125 pli	Stainless Steel, 90° peel, 12"/min, 2 mil aluminum, 72 hr at 70°C; ASTM D3330
	1.249 kN/m	7.125 pli	Polycarbonate, 90° peel, 12"/min, 2 mil aluminum, 72 hr at 70°C; ASTM D3330

Thermal Properties	Metric	English	Comments
CTE, linear	58.0 $\mu\text{m/m-}^{\circ}\text{C}$	32.2 $\mu\text{in/in-}^{\circ}\text{F}$	Second heat; ASTM-D696
	20.0 $\mu\text{m/m-}^{\circ}\text{C}$ @Thickness 0.0508 mm	11.1 $\mu\text{in/in-}^{\circ}\text{F}$ @Thickness 0.00200 in	First heat; ASTM-D696

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.21	3.21	0.040 thickness; ASTM D-150-92
	@Frequency 1000 Hz	@Frequency 1000 Hz	

Electrical Properties	Metric	English	Comments
Dielectric Strength	13.4 kV/mm	340 kV/in	500 VAC, 60 Hz, [60 Hz]/sec; ASTM D149-92
	@Thickness 0.0508 mm	@Thickness 0.00200 in	
Dissipation Factor	0.040	0.040	
	@Thickness 0.0508 mm	@Thickness 0.00200 in	

Processing Properties	Metric	English	Comments
Shelf Life	18.0 Month	18.0 Month	

Descriptive Properties	Value	Comments
Adhesive Type	300	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China