

3M Scotchkote™ SG 527 Epoxy Metal Repair

Category: Polymer, Thermoset, Epoxy

Material Notes:

Scotchkote Epoxy Metal Repair SG 527 is a specially packaged rapid curing synthetic metal repair compound for on site repairs to metal components such as leaking pipes, tanks, ducts, and radiators. Product Features: Simple to use, only requiring simple hand mixing to activate reaction between the concentrically packed components Designed for application by gloved hand, putty knife or spatula Can be applied to any damaged metal surface, plus glass, fiberglass and other composite surfaces Designed for rapid repairs to cracked casting, leaking pipes, tanks, flanges etc. minimizing downtime Excellent adhesion to correctly prepared metal surfaces. Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Scotchkote-SG-527-Epoxy-Metal-Repair.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------|---------|----------|
| Solids Content | 100 % | 100 % | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|----------|----------|--|
| Flexural Strength | 22.4 MPa | 3250 psi | |
| Compressive Strength | 34.5 MPa | 5000 psi | |
| Shear Strength | 4.48 MPa | 650 psi | Tensile Shear Adhesion, on a grit blasted steel |

| Thermal Properties | Metric | English | Comments |
|-----------------------------|---------|---------|----------|
| Heat Distortion Temperature | 40.0 °C | 104 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|----------|------------|------------------------|
| Cure Time | 30.0 min | 0.500 hour | Hard Dry for machining |
| | 120 min | 2.00 hour | Full Cure |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Appearance | Gray | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China