

A. Schulman ComAlloy Aqualoy® 134 Polypropylene, Glass Reinforced, Chemically Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 40% Glass Reinforced. In Aqualoy® materials, carefully selected base resins and proprietary additives meld hydrolytic stability and high strength traits into a unique property blend. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Aqualoy-134-Polypropylene-Glass-Reinforced-Chemically-Coupled.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	107	107	ASTM D785
Tensile Strength, Ultimate	81.0 MPa	11700 psi	ASTM D638
Elongation at Break	4.4 %	4.4 %	ASTM D638
Flexural Strength	119 MPa	17300 psi	ASTM D790
Flexural Modulus	6.00 GPa	870 ksi	ASTM D790
Izod Impact, Notched	0.910 J/cm	1.70 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.95 J/cm	7.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	166 °C	331 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	136 °C	277 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	229 - 246 °C	444 - 475 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China