

A. Schulman ComAlloy Comtuf® 525 Polycarbonate/Styrenic Alloy

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Styrenic Alloy , Polystyrene (PS)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. Superior toughness and impact resistance characterize Comtuf® materials. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Comtuf-525-PolycarbonateStyrenic-Alloy.php

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in ³	
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	92	92	ASTM D785
Tensile Strength, Ultimate	48.0 MPa	6960 psi	ASTM D638
Elongation at Break	14 %	14 %	ASTM D638
Flexural Strength	68.0 MPa	9860 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	6.57 J/cm	12.3 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	109 °C	228 °F	ASTM D648
Glass Transition Temp, Tg	145 - 150 °C	293 - 302 °F	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	246 - 277 °C	475 - 531 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China