

A. Schulman ComAlloy Comtuf® 633 Nylon 6/6, Glass Reinforced, Impact Modified, Flow Enhanced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Reinforced, Impact Grade

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 30% Glass Reinforced. Superior toughness and impact resistance characterize Comtuf® materials. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Comtuf-633-Nylon-66-Glass-Reinforced-Impact-Modified-Flow-Enhanced.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	112 MPa	16200 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Flexural Strength	143 MPa	20700 psi	ASTM D790
Flexural Modulus	6.20 GPa	899 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm	2.40 ft-lb/in	ASTM D256
Izod Impact, Unnotched	7.53 J/cm	14.1 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	229 °C	444 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	204 °C	399 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	290 °C	554 °F	Approximate middle barrel temperature.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China