

A. Schulman ComAlloy Comtuf® 652 Nylon 6/6, Mineral Reinforced, Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Mineral Filled, Impact Grade

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 30% Mineral Reinforced. Superior toughness and impact resistance characterize Comtuf® materials. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Comtuf-652-Nylon-66-Mineral-Reinforced-Impact-Modified.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Ultimate	63.0 MPa	9140 psi	ASTM D638
Elongation at Break	18 %	18 %	ASTM D638
Flexural Strength	103 MPa	14900 psi	ASTM D790
Flexural Modulus	3.60 GPa	522 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	230 °C	446 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	290 °C	554 °F	Approximate middle barrel temperature.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China