

**A. Schulman SCHULADUR® A GB30 30% Glass Bead Reinforced PBT**

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Bead Filled

**Material Notes:**

Information provided by A. Schulman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-SCHULADUR-A-GB30-30-Glass-Bead-Reinforced-PBT.php](http://www.lookpolymers.com/polymer_A-Schulman-SCHULADUR-A-GB30-30-Glass-Bead-Reinforced-PBT.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Linear Mold Shrinkage	0.015 cm/cm @Thickness 3.175 mm	0.015 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	49.6 MPa	7200 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	4.48 GPa	650 ksi	ASTM D790
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.94 J/cm	5.50 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	182 °C	360 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	138 °C	280 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 260 °C	482 - 500 °F	
Mold Temperature	30.0 - 65.6 °C	86.0 - 150 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**