

A. Schulman SCHULADUR® A GF15 15% Glass Fiber Reinforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Bead Filled

Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-SCHULADUR-A-GF15-15-Glass-Fiber-Reinforced-PBT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm @Thickness 3.175 mm	0.0060 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	96.5 MPa	14000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	159 MPa	23000 psi	ASTM D790
Flexural Modulus	5.86 GPa	850 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm	1.30 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.14 J/cm	11.5 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	193 °C	380 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 260 °C	482 - 500 °F	
Mold Temperature	30.0 - 65.6 °C	86.0 - 150 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China