

A. Schulman SCHULAMID® 6 GF15H 30% Glass Fiber Reinforced Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-SCHULAMID-6-GF15H-30-Glass-Fiber-Reinforced-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Linear Mold Shrinkage	0.0020 cm/cm @Thickness 3.175 mm	0.0020 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	158 MPa	22900 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Flexural Strength	221 MPa	32000 psi	ASTM D790
Flexural Modulus	8.818 GPa	1279 ksi	ASTM D790
Izod Impact, Notched	1.12 J/cm	2.10 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.01 J/cm	15.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	218 °C	425 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	202 °C	396 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 295 °C	518 - 563 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Drying Temperature	79.4 °C	175 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China