

AFE Technologies Cronite 37Ni/18Cr/Nb No. HR32

Category : Metal , Superalloy , Iron Base

Material Notes:

High temperature nickel alloy castings. Applications include heat treatment and handling products, furnace products, tubes, power generation, and petrochemical industries. Information provided by AFE Technologies/North American Cronite, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_AFE-Technologies-Cronite-37Ni18CrNb-No-HR32.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	480 MPa	69600 psi	As Cast
Tensile Strength, Yield	250 MPa	36300 psi	As Cast
Elongation at Break	8.0 %	8.0 %	As Cast; 5.65 A^{0.5}
Rupture Strength	3.40 MPa	493 psi	Stress Rupture
	@Temperature 1150 °C, Time 3.60e+7 sec	@Temperature 2100 °F, Time 10000 hour	
	5.30 MPa	769 psi	Stress Rupture
	@Temperature 1100 °C, Time 3.60e+7 sec	@Temperature 2010 °F, Time 10000 hour	
	8.00 MPa	1160 psi	Stress Rupture
	@Temperature 1050 °C, Time 3.60e+7 sec	@Temperature 1920 °F, Time 10000 hour	
	12.0 MPa	1740 psi	Stress Rupture
	@Temperature 1000 °C, Time 3.60e+7 sec	@Temperature 1830 °F, Time 10000 hour	
	18.0 MPa	2610 psi	Stress Rupture
	@Temperature 950 °C, Time 3.60e+7 sec	@Temperature 1740 °F, Time 10000 hour	
25.0 MPa	3630 psi	Stress Rupture	
@Temperature 900 °C, Time 3.60e+7 sec	@Temperature 1650 °F, Time 10000 hour		
34.0 MPa	4930 psi	Stress Rupture	
@Temperature 850 °C, Time 3.60e+7 sec	@Temperature 1560 °F, Time 10000 hour		
45.0 MPa	6530 psi	Stress Rupture	
@Temperature 800 °C, Time 3.60e+7 sec	@Temperature 1470 °F, Time 10000 hour		

Mechanical Properties	59.0 MPa Metric	8560 psi English	Comments Stress Rupture
	@Temperature 750 °C, Time 3.60e+7 sec	@Temperature 1380 °F, Time 10000 hour	
	78.0 MPa	11300 psi	
	@Temperature 700 °C, Time 3.60e+7 sec	@Temperature 1290 °F, Time 10000 hour	Stress Rupture

Component Elements Properties	Metric	English	Comments
Carbon, C	0.40 %	0.40 %	
Chromium, Cr	18 %	18 %	
Iron, Fe	40.6 %	40.6 %	As Remainder
Manganese, Mn	1.0 %	1.0 %	
Nickel, Ni	37 %	37 %	
Niobium, Nb (Columbium, Cb)	1.5 %	1.5 %	
Silicon, Si	1.5 %	1.5 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China