

AK Steel ZINCGRIP® ELECTRASMOOTH® Electrogalvanized Carbon Steel, Dent Resistant (DR 210)

Category : Metal , Ferrous Metal , Carbon Steel , Low Carbon Steel

Material Notes:

Compared to DS Type B, DR steels have higher initial YS which contributes to increased strength after forming. Information provided by AK Steel

Order this product through the following link:

http://www.lookpolymers.com/polymer_AK-Steel-ZINCGRIP-ELECTRASMOOTH-Electrogalvanized-Carbon-Steel-Dent-Resistant-DR-210.php

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	>= 359 MPa	>= 52100 psi	
Tensile Strength, Yield	>= 228 MPa	>= 33100 psi	
Elongation at Break	>= 36 %	>= 36 %	
Modulus of Elasticity	200 GPa	29000 ksi	

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	0.481 J/g-°C	0.115 BTU/lb-°F	
	@Temperature 50.0 - 100 °C	@Temperature 122 - 212 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000142 ohm-cm	0.0000142 ohm-cm	

Descriptive Properties	Value	Comments
Deep-Drawing Capability rm	1.8	
Strain Hardening Exponent n	0.2	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China