

AK Steel ZINCGRIP® Hot Dip Galvanized Carbon Steel, Extra Deep Drawing Steel (EDDS), Standard Grade

Category : Metal , Ferrous Metal , Carbon Steel , Low Carbon Steel

Material Notes:

Interstitial Free (I-F®) steels are made by adding titanium and/or columbium to the molten steel after vacuum degassing and offer excellent drawability. Information provided by AK Steel

Order this product through the following link:

http://www.lookpolymers.com/polymer_AK-Steel-ZINCGRIP-Hot-Dip-Galvanized-Carbon-Steel-Extra-Deep-Drawing-Steel-EDDS-Standard-Grade.php

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	310 MPa	45000 psi	.0275 - .035 inches sheet thickness; ASTM A 370
Tensile Strength, Yield	165 MPa	23900 psi	.0275 - .035 inches sheet thickness; ASTM A 370
Elongation at Break	44 %	44 %	.0275 - .035 inches sheet thickness; ASTM A 370
Modulus of Elasticity	200 GPa	29000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	12.9 µm/m-°C	7.17 µin/in-°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
Specific Heat Capacity	0.481 J/g-°C	0.115 BTU/lb-°F	
	@Temperature 50.0 - 100 °C	@Temperature 122 - 212 °F	
Thermal Conductivity	93.0 W/m-K	645 BTU-in/hr-ft ² -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000142 ohm-cm	0.0000142 ohm-cm	

Descriptive Properties	Value	Comments
Deep-Drawing Capability rm	1.6	.0275 - .035 inches sheet thickness
Strain Hardening Exponent n	0.23	.0275 - .035 inches sheet thickness

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China