

ATG s.r.l. ACM Polyacrylic Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATG-srl-ACM-Polyacrylic-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc	1.11 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50 - 90	50 - 90	
Tensile Strength, Ultimate	5.00 - 14.0 MPa	725 - 2030 psi	
Elongation at Break	100 - 350 %	100 - 350 %	
Rebound	5.0 - 8.0 %	5.0 - 8.0 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	170 °C	338 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	

Descriptive Properties	Value	Comments
Abrasion Resistance	low	
Chemical Resistance to Animal and Vegetable Oils and Greases	high	
Chemical Resistance to Aromatic Hydrocarbons	none	
Chemical Resistance to Chloride Solvents	none	
Chemical Resistance to Distilled Water	low	
Chemical Resistance to Ketones	none	
Chemical Resistance to Maximum Concentrated Alkalis (at 50°C)	low	
Chemical Resistance to Medium-High Concentrated Acids (at 50°C)	low	
Chemical Resistance to Mineral Oils and Aliphatic Hydrocarbons	high	
Compression set at 100°C	high	
Impermeability at gas (Oxygen and Nitrogen)	medium	

Resistance to Flame Descriptive Properties	Value	Comments
Resistance to Heat Aging	high	
Resistance to Low Temperatures	low	
Resistance to Ozone and Weathering	high	
Tear Strength	low	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China