

ATG s.r.l. NR Natural Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATG-srl-NR-Natural-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	25 - 95	25 - 95	
Tensile Strength, Ultimate	14.0 - 30.0 MPa	2030 - 4350 psi	
Elongation at Break	150 - 850 %	150 - 850 %	
Rebound	30 - 65 %	30 - 65 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	85.0 °C	185 °F	
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	

Descriptive Properties	Value	Comments
Abrasion Resistance	high	
Chemical Resistance to Animal and Vegetable Oils and Greases	none	
Chemical Resistance to Aromatic Hydrocarbons	none	
Chemical Resistance to Chloride Solvents	none	
Chemical Resistance to Distilled Water	low	
Chemical Resistance to Ketones	medium	
Chemical Resistance to Maximum Concentrated Alkalis (at 50°C)	medium	
Chemical Resistance to Medium-High Concentrated Acids (at 50°C)	low	
Chemical Resistance to Mineral Oils and Aliphatic Hydrocarbons	none	
Compression set at 100°C	medium	
Impermeability at gas (Oxygen and Nitrogen)	medium	

Resistance to Flame Descriptive Properties	Value	Comments
Resistance to Heat Aging	low	
Resistance to Low Temperatures	medium	
Resistance to Ozone and Weathering	medium	
Tear Strength	high	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China