

ATI Wah Chang Nb/Nb Alloy FS-85

Category : Metal , Nonferrous Metal , Niobium Alloy

Material Notes:

Information provided by ATI Wah Chang

Order this product through the following link:

http://www.lookpolymers.com/polymer_ATI-Wah-Chang-NbNb-Alloy-FS-85.php

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	140 GPa	20300 ksi	
	110 GPa	16000 ksi	
	@Temperature 1200 °C	@Temperature 2190 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	52.7 W/m-K	366 BTU-in/hr-ft ² -°F	
	@Temperature 800 °C	@Temperature 1470 °F	
	56.6 W/m-K	393 BTU-in/hr-ft ² -°F	
	@Temperature 1200 °C	@Temperature 2190 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China