

Aaron Industries AAROLENE® ARPE HD 300-2 Black BM High Density Polyethylene, Blow Molding

Category: Polymer, Thermoplastic, Polyethylene (PE), HDPE, High Density Polyethylene (HDPE), Blow Molding Grade

Material Notes:

AAROLENE® ARPE 300 Series Polyethylene Compounded Resin, HDPE Black, Blow Molding GradeFeatures: A high density Polyethylene compound, pre-colored black, specifically designed for all blow molding and pipe applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aaron-Industries-AAROLENE-ARPE-HD-300-2-Black-BM-High-Density-Polyethylene-Blow-Molding.php

| Physical Properties | Metric | English | Comments |
|-----------------------|---------------|---------------|------------|
| Specific Gravity | 0.953 g/cc | 0.953 g/cc | ASTM D792 |
| Linear Mold Shrinkage | 0.015 cm/cm | 0.015 in/in | ASTM D955 |
| Melt Flow | 0.40 g/10 min | 0.40 g/10 min | ASTM D1238 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|-----------|----------|-----------|
| Tensile Strength, Yield | 26.9 MPa | 3900 psi | ASTM D638 |
| Flexural Modulus | 0.814 GPa | 118 ksi | ASTM D790 |
| Izod Impact, Notched | NB | NB | ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|--|---------|---------|-----------|
| Deflection Temperature at 0.46 MPa (66 psi) | 76.7 °C | 170 °F | ASTM D648 |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China