

Aaron Industries AVPP H 200-1 Virgin Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Melt flow index may be specified.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aaron-Industries-AVPP-H-200-1-Virgin-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	ASTM D792
Linear Mold Shrinkage	0.022 cm/cm	0.022 in/in	ASTM D955
Melt Flow	8.0 - 12 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 - 12 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	31.0 MPa	4500 psi	ASTM D638
Flexural Modulus	1.38 GPa	200 ksi	ASTM D790
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	128 °C	262 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China