

Aclo Accutech Polycarbonate POL050G40L Glass Reinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 40% Glass Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polycarbonate-POL050G40L-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
Ash	40 %	40 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength at Break	139.0 MPa	20160 psi	ASTM D638
Tensile Strength, Yield	140 MPa	20300 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	5.499 GPa	797.6 ksi	ASTM D638
Flexural Strength	215.0 MPa	31180 psi	ASTM D790
Flexural Modulus	10.998 GPa	1595.1 ksi	ASTM D790
Izod Impact, Notched	1.76 J/cm	3.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	145 °C	293 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China