

Aclo Accutech Polycarbonate POL051G30L Glass Reinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 30% Glass Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polycarbonate-POL051G30L-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	MD; ASTM D955
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
Ash	30 %	30 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength at Break	122.0 MPa	17690 psi	ASTM D638
Tensile Strength, Yield	123.0 MPa	17840 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	5.399 GPa	783.1 ksi	ASTM D638
Flexural Strength	200 MPa	29000 psi	ASTM D790
Flexural Modulus	8.5985 GPa	1247.1 ksi	ASTM D790
Izod Impact, Notched	1.71 J/cm	3.20 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	144 °C	291 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China