

Aclo Accutech Polypropylene Copolymer CP0436C20L Calcium Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Calcium Carbonate (CaCO3) Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Aclo-Accutech-Polypropylene-Copolymer-CP0436C20L-Calcium-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.011 cm/cm	0.011 in/in	MD; ASTM D955
Melt Flow	11 g/10 min	11 g/10 min	ASTM D1238
Ash	20 %	20 %	ASTM D2584

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	58	58	ASTM D785
Tensile Strength at Break	16.0 MPa	2320 psi	ASTM D638
Tensile Strength, Yield	21.0 MPa	3050 psi	ASTM D638
Elongation at Break	53 %	53 %	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Tensile Modulus	1.40 GPa	203 ksi	ASTM D638
Flexural Strength	25.0 MPa	3630 psi	ASTM D790
Flexural Modulus	1.20 GPa	174 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	55.0 °C	131 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	92.2 °C	198 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China